

M.S.FLATS WEIGHT PER METRE IN K.G.

Thickness MM	5	6	8	10	1	26	118	20	22	25
12	05	0.6	0.8	0.9	1.1	1.5	1.7	1.9	2.1	2.4
16	0.6	0.8	1.0	1.3	1.5	2.0	2.3	2.5	2.8	3.1
20	0.8	0.9	1.3	1.6	1.9	2.5	2.8	3.1	3.5	3.9
25	*	1.2	1.6	2.0	2.4	3.1	3.5	3.9	4.3	4.9
32	1.3	1.5	2.0	2.4	3.0	4.0	4.5	5.0	5.5	6.3
35	*	1.6	*	2.8	*	*	*	*	*	*
40	1.6	1.9	2.5	3.1	3.8	5.0	5.7	6.3	6.9	7.8
45	*	2.1	*	3.5	4.2	*	*	*	*	*
50	2.0	2.4	3.1	3.9	4.7	6.3	7.1	7.8	8.6	9.8
53	*	*	*	*	*	6.6	*	*	*	*
56	*	*	*	*	*	7.0	*	*	*	*
63	2.5	3.0	4.0	4.9	5.9	7.9	8.9	9.9	10.9	12.4
65	*	3.2	4.1	5.1	6.1	*	*	10.2	*	*
70	*	3.6	4.7	5.9	7.1	*	*	11.8	*	14.7
80	3.1	3.8	5.0	6.3	7.5	10.0	11.3	12.6	13.8	15.7
100	3.9	4.7	6.3	7.8	9.4	12.6	14.0	15.7	17.5	19.6
110	*	*	*	*	*	*	*	17.3	*	*
125	4.9	5.9	7.8	9.8	11.8	15.7	17.7	19.6	21.6	24.5
150	*	*	*	*	14.1	*	18.8	23.6	*	29.4
160	6.3	7.5	10.0	12.6	15.1	20.1	22.6	25.1	27.6	31.4
180	*	*	*	*	17.0	22.6	25.4	28.3	*	*
200	7.8	9.4	12.6	15.7	18.8	25.1	28.3	31.4	34.5	39.2
220	*	*	*	*	*	*	*	34.5	*	*
250	9.8	11.3	15.7	19.6	23.6	31.4	35.3	39.2	43.2	49.1